

آتش پویا سپاهان

ATASH POOYA SEPAHAN

تولید کننده فرآورده های نسوز صنعتی
در ابعاد و اندازه های مختلف



ATASHPOOYA REFRACTORIES CO. APCO - D50

General Properties

Classification	Medium Alumina Brick
Raw Material Basis	Bauxite – Chamotte
Bond	Ceramic
Packaging	Pallet
Storage Life(Month)	No expiration date

Main Chemical Component

Al ₂ O ₃ (%)	SiO ₂ (%)	Fe ₂ O ₃ (%)	TiO ₂ (%)
47-50	42-45	2.0-3.0	3.5-4.5

Physical & Thermal Properties

Refractory Under Load T05	1330
Bulk Density (gr/cm ³)	2.25-2.35
Cold Crushing Strength (Kg/cm ²)	400-600