

آتش پویا سپاهان

ATASH POOYA SEPAHAN

تولید کننده فرآورده های نسوز صنعتی
در ابعاد و اندازه های مختلف



ATASHPOOYA REFRACTORIES CO. APCO - D70SP

General Properties

Classification	High Alumina Brick
Description	High mechanical, abrasion and thermal resistance
Raw Material Basis	Bauxite (Rotary Kiln)
Bond	Phosphate Bonded
Packaging	Pallet
Storage Life (Month)	No expiration date

Main Chemical Component

Al ₂ O ₃ (%)	SiO ₂ (%)	Fe ₂ O ₃ (%)	TiO ₂ (%)
67-70	21-23	2.0-3.0	2.8-3.8

Physical & Thermal Properties

Refractory Under Load T05 (°C)	1400
Bulk Density (gr/cm ³)	2.4-2.6
Cold Crushing Strength (Kg/cm ²)	550-750